# ORAJET 3951

# **Description**

Premium Cast PVC film, white and transparent, gloss surface

#### Release paper

PE-coated silicone paper, 148g/m<sup>2</sup>, 168 μm

#### Adhesive

Solvent polyacrylate, repositionable, permanent, grey and transparent

### Area of use

For long-term displays with the highest degree of brillancy and durability in outdoor applications, e.g. complete car wrapping.

# **Printing method**

Solventbased inkjet printing

#### **Technical data**

1 Clinical data	
Thickness* (without protective paper and adhesive)	55 micron
<b>Dimensional stability</b> (FINAT TM 14)	adhered to steel, no shrinkage in cross direction, in length 0.1 mm max.
Temperature resistance	adhered to aluminium, -50°C to +100°C, no variation
Seawater resistance (DIN 50021)	adhered to aluminium, after 100h/23°C no variation
Resistance to solvents and chemicals	at room temperature, 72h after adhesion to aluminium, short- term resistant to most oils and greases, fuels, aliphatic solvents, weak acids, salts and alkalis
Fire behavior (DIN 4102-1)	Only flame resistant (class DIN 4102-B1) on steel surface (indoor application, also printed)
Adhesive power*	18N/25 mm
(FINAT TM 1, after 24h, stainless steel)	
Tensile strength (DIN EN ISO 527)	
along	min. 19 MPa
across	min. 19 MPa
Elongation at break (DIN EN ISO 527)	
along	min. 120%
across	min. 120%
Shelf life**	2 years
Application temperature	>+8°C
Service life by specialist application	White: 10 years (not printed)
under vertical outdoor exposure (normal climate of Central Europe)	Transparent: 8 years (not printed)
* **	1.00

# **Attention:**

After printing the ink must be thoroughly dry in order to avoid any affect on the later combination with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.



ORAFOL Europe GmbH - Am Biotop 2 - D 16515 Oranienburg Telefon: +49 (0) 33 01/864 0 - Telefax: +49 (0) 33 01/864 100 E-Mail: verkauf@orafol.de - Internet: http://www.orafol.d